



Quality:	BISAM	Collection:	Projection
Construction:	Tufted 1/10" saxonyvelours, uni	Pile material:	100% Polyamid
Backing:	Textile backing actionbac	Carrier material:	PP-Tapes




 06
1658-CPD-1018
Vorwerk & Co. Teppichwerke
GmbH & Co. KG
Kuhlmannstrasse 11
D - 31785 Hameln
EN 14041: 2004


EN 1307



Gauge /10 cm	approx.	39,5	Pile weight g/m ²	approx.	1070
Tufts /10 cm	approx.	52	Primary backing weight g/m ²	approx.	95
Points /dm ²	approx.	2054	Total weight g/m ²	approx.	1770
Pile thickness /mm	approx.	5,6	Weight of backing g/m ²	approx.	740
Total thickness /mm	approx.	7,6	Weight of pile material g/m ²	approx.	820
			Pile density g/cm ³	approx.	0,150

Castor chair test	DIN EN 985	$r \geq 2,0$							
Sound impact	DIN EN ISO 717-2	verklebt ΔL_w	27 dB						
Sound absorbtion	DIN EN ISO 354	Hz	125	250	500	1.000	2.000	4.000	
	verklebt	α_s							
Heat flux	DIN ISO 8302: 1991	$1/\lambda =$	0,11	m ² K/W					
		Suitable for glueing on underfloor heating systems.							
Fire rating	DIN EN 13501-1	$C_{fl} -S1$							

Static resistance	DIN EN 1815 Bl. 2	< 2,0	KV	b. 25% rel. F.
Surface resistance	DIN ISO/DIS 10965 Bl. 1 R _{OT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Vertical resistance	DIN ISO/DIS 10965 Bl. 1 R _{DT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Resistance to ground	DIN ISO/DIS 10965 R _{ET}		Ω	b. 25% rel. F.
Fastness to water	DIN EN ISO 105-E 01 Colour-changes		N. 4	
Fastness to light	DIN EN ISO 105-B 02		N. 5	
Fastness to rubbing	DIN EN ISO 105-X 12		N. 4	

This quality is suitable for fitting on subfloors with underfloor heating when fully glued with suitable dispersion adhesive. To avoid changes in measurements we recommend total glueing (dispersion adhesives). Laying instructions: refer to our current cleaning and fitting instructions. Due to constant improvements and further developments of our products, we reserve the right to adapt our technical details accordingly.