

Quality:	DACAPO	Collection:	Fascination
Construction:	1/10" tuftet velours, tuft patterned	Pile material:	100% polyamide
Backing:	Texback®super	Carrier material:	PES-Fleece



CE
1658-CPD-1021
Vorwerk & Co. Teppichwerke
GmbH & Co. KG
Kuhlmannstrasse 11
D – 31785 Hameln
EN 14041: 2004

EN 1307



Gauge / 10 cm	ca.	39,5	Pile inset weight g/m ²	ca.	950
Tufts / 10 cm	ca.	48	Primary backing weight g/m ²	ca.	130
Points dm ²	ca.	1847	Total weight g/m ²	ca.	1840
Pile thickness mm	ca.	5,0	Weight of backing g/m ²	ca.	715
Total thickness mm	ca.	8,0	Weight of pile material g/m ²	ca.	630
			Pile density g/cm ³	ca.	0,130

Castor chair test	DIN EN 985	r ≥ 2,4							
Sound impact	DIN EN ISO 717-2	glued Δ Lw	28 dB						
Sound absorption	DIN EN ISO 354	Hz	125	250	500	1.000	2.000	4.000	
	verklebt	αs	0,02	0,05	0,12	0,26	0,48	0,68	
Heat flux	DIN ISO 8302: 1991	1/λ =	0,13	m ² K/W					
Fire rating	DIN EN 13501-1	C _{fl} –S1	not glued, glued or burred						

Static resistance	DIN EN 1815 Bl. 2	< 2,0	KV	b. 25% rel. F.
Surface resistance	DIN ISO/DIS 10965 Bl. 1 R _{OT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Vertical resistance	DIN ISO/DIS 10965 Bl. 1 R _{DT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Fastness to water	DIN EN ISO 105-E 01 Colour-changes	N. 4		
Fastness to light	DIN EN ISO 105-B 02	N. 5		
Fastness to rubbing	DIN EN ISO 105-X 12	N. 4		

This good is applicable for laying on floors with floor heating when adhesion covers all the surface and dispersion adhesive was used which is resisting heat and deterioration. In order to avoid change of measure we recommend a fixes laying (glued with dispersion adhesive or burred with the Vorwerk Ecofix® system). Laying manual: see current maintenance and laying manual. Because of permanent further development and improvement of quality change of technical data is reserved.