



Quality:	FORMA design	Collection:	Projection
Construction:	Tufted 5/64"velours, printed	Pile material:	100% Polyamid
Backing:	Textile backing actionbac	Carrier material:	PES-Fleece



Gauge /10 cm	approx.	50	Pile weight g/m ²	approx.	700
Tufts /10 cm	approx.	70	Primary backing weight g/m ²	approx.	120
Points /dm ²	approx.	3500	Total weight g/m ²	approx.	1440
Pile thickness /mm	approx.	4,2	Weight of backing g/m ²	approx.	650
Total thickness /mm	approx.	6,0	Weight of pile material g/m ²	approx.	512
			Pile density g/cm ³	approx.	0,123

Castor chair test	DIN EN 985	$r \geq 2,4$							
Sound impact	DIN EN ISO 717-2	verklebt ΔLw	27 dB						
Sound absorbtion	DIN EN ISO 354	Hz	125	250	500	1.000	2.000	4.000	
	verklebt	α_s	0,01	0,02	0,09	0,21	0,38	0,54	
Heat flux	DIN ISO 8302: 1991	$1/\lambda =$	0,11	m ² K/W					
Fire rating	Suitable for glueing on underfloor heating systems.								
	DIN EN 13501-1	$C_{fl} -S1$							

Static resistance	DIN EN 1815 Bl. 2	< 2,0	KV	b. 25% rel. F.
Surface resistance	DIN ISO/DIS 10965 Bl. 1 R _{OT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Vertical resistance	DIN ISO/DIS 10965 Bl. 1 R _{DT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Resistance to ground	DIN ISO/DIS 10965 R _{ET}		Ω	b. 25% rel. F.
Fastness to water	DIN EN ISO 105-E 01 Colour-changes		N. 4	
Fastness to light	DIN EN ISO 105-B 02		N. 5	
Fastness to rubbing	DIN EN ISO 105-X 12		N. 4	

This quality is suitable for fitting on subfloors with underfloor heating when fully glued with suitable dispersion adhesive.
To avoid changes in measurements we recommend total glueing (dispersion adhesives). Laying instructions: refer to our current cleaning and fitting instructions. Due to constant improvements and further developments of our products, we reserve the right to adapt our technical details accordingly.