



Quality:	NANDOU/-design 2chorig	Collection:	Projection
Construction:	Woven loop pile, uni/ patterned	Pile material:	100% Polyamid
Backing:	Conductive latex backing	Carrier material:	PES-Ware/ PP-Weft




 06
1658-CPD-1023
Vorwerk & Co. Teppichwerke
GmbH & Co. KG
Kuhlmannstrasse 11
D - 31785 Hameln
EN 14041: 2004


EN 1307



Gauge /10 cm	approx.	28	Pile weight g/m ²	800
Tufts /10 cm	approx.	30	Primary backing weight g/m ²	approx. 490
Points /dm ²	approx.	840	Total weight g/m ²	approx. 1600
Pile thickness /mm	approx.	2,3	Weight of backing g/m ²	approx. 310
Total thickness /mm	approx.	4,5	Weight of pile material g/m ²	approx. 450
			Pile density g/cm ³	approx. 0,196

Castor chair test	DIN EN 985	$r \geq 2,4$							
Sound impact	DIN EN ISO 717-2	verklebt ΔL_w	20dB						
Sound absorbtion	DIN EN ISO 354	Hz	125	250	500	1.000	2.000	4.000	
	verklebt	α_s	--	0,03	0,04	0,11	0,23	0,37	
Heat flux	DIN ISO 8302: 1991	$1/\lambda =$	0,05	m ² K/W					
Fire rating	Suitable for glueing on underfloor heating systems.								
	DIN EN 13501-1	$C_{fl} -S1$							

Static resistance	DIN EN 1815 Bl. 2	< 2,0	KV	b. 25% rel. F.
Surface resistance	DIN ISO/DIS 10965 Bl. 1 R _{OT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Vertical resistance	DIN ISO/DIS 10965 Bl. 1 R _{DT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Resistance to ground	DIN ISO/DIS 10965 R _{ET}		Ω	b. 25% rel. F.
Fastness to water	DIN EN ISO 105-E 01 Colour-changes		N. 4	
Fastness to light	DIN EN ISO 105-B 02		N. 5	
Fastness to rubbing	DIN EN ISO 105-X 12		N. 4	

This quality is suitable for fitting on subfloors with underfloor heating when fully glued with suitable dispersion adhesive.
 To avoid changes in measurements we recommend total glueing (dispersion adhesives). Laying instructions: refer to our current cleaning and fitting instructions. Due to constant improvements and further developments of our products, we reserve the right to adapt our technical details accordingly.