



Quality:	TREMO 900 S.D.	Collection:	Projection
Construction:	Tufted 1/10" velours, Solution Dyed	Pile material:	100% Polyamid
Backing:	Textile backing actionbac	Carrier material:	PES-Fleece




 06
1658-CPD-1020
**Vorwerk & Co. Teppichwerke
 GmbH & Co. KG**
 Kuhlmannstrasse 11
 D – 31785 Hameln
EN 14041: 2004


EN 1307



Gauge /10 cm	approx.	39,5	Pile weight g/m²	approx.	900
Tufts /10 cm	approx.	47	Primary backing weight g/m²	approx.	130
Points /dm²	approx.	1857	Total weight g/m²	approx.	1650
Pile thickness /mm	approx.	3,6	Weight of backing g/m²	approx.	650
Total thickness /mm	approx.	6,3	Weight of pile material g/m²	approx.	520
			Pile density g/cm³	approx.	0,144

Castor chair test	DIN EN 985	$r \geq 2,4$							
Sound impact	DIN EN ISO 717-2	verklebt ΔL_w	27 dB						
Sound absorption	DIN EN ISO 354	verklebt α_s	Hz	125	250	500	1.000	2.000	4.000
				0,01	0,03	0,09	0,22	0,41	0,58
Heat flux	DIN ISO 8302: 1991	$1/\lambda =$	0,09	$m^2 K/W$					
		Suitable for glueing on underfloor heating systems.							
Fire rating	DIN EN 13501-1	$C_{fl} -S1$							

Static resistance	DIN EN 1815 Bl. 2	< 2,0	KV	b. 25% rel. F.
Surface resistance	DIN ISO/DIS 10965 Bl. 1 R _{OT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Vertical resistance	DIN ISO/DIS 10965 Bl. 1 R _{DT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Resistance to ground	DIN ISO/DIS 10965 R _{ET}		Ω	b. 25% rel. F.
Fastness to water	DIN EN ISO 105-E 01 Colour-changes		N. 4	
Fastness to light	DIN EN ISO 105-B 02		N. 5	
Fastness to rubbing	DIN EN ISO 105-X 12		N. 4	

This quality is suitable for fitting on subfloors with underfloor heating when fully glued with suitable dispersion adhesive. To avoid changes in measurements we recommend total glueing (dispersion adhesives). Laying instructions: refer to our current cleaning and fitting instructions. Due to constant improvements and further developments of our products, we reserve the right to adapt our technical details accordingly.