

Bertola / Bruna GlasBac® RE Tile

Style#: 12317

Color#: 8816

Carpet Type: Tile

Standard Size: 50 cm x 50 cm (19.69 in x 19.69 in)

Backing Options: GlasBac® RE Tile (50 cm x 50 cm), GlasBac® Tile (50 cm x 50 cm), NexStep® Tile (50 cm x 50 cm)

Layout Options:



Specifications for GlasBac® RE Tile


Product Number:	123178816
Product Construction:	Tufted Cut & Loop
Soil/Stain Protection:	Protekt®
Antimicrobial Treatment:	(AATCC 138 Washed) (AATCC 174 Parts 2&3) Intersept®
Yarn System:	Post-Consumer Content Type 6,6 Nylon
Yarn Manufacturer:	Universal
Dye Method:	100% Solution Dye
Post-Industrial:	40% - 40%
Post-Consumer:	26%
Total Recycled Content:	66% - 66%


Product Specifications	U.S.	Metric
Tufted Yarn Weight:	23 oz/yd ²	780 g/m ²
Machine Gauge:	5/64 in	50.4 ends/10 cm
Pile Height:	.14 in	3.6 mm
Pile Thickness:	.127	3.2
Stitches:	12/in	47.244 ends/10cm
Pile Density:	6520	
Size:	19.69 in x 19.69 in	50 cm x 50 cm

Performance Specifications


Indoor Air Quality:	Green Label Plus Certified #GLP0820
Sustainable Carpet Assessment Standard:	NSF-140 Platinum
Radiant Panel:	(ASTM E-648) Class 1
Smoke Density:	
Lightfastness:	(AATCC 16 - E)
Static:	(AATCC - 134) < 3.0 KV

Other Colors for Bertola







Olivastro
Color#: 8825




Verde
Color#: 8826




Muschio
Color#: 8827




Grigio
Color#: 8829



Tempesta
Color#: 8830



Azzuro
Color#: 8831



Carbone
Color#: 8832



Ardesia
Color#: 8833

All Product Specifications are averages derived from product sample testing and are subject to normal manufacturing tolerances and testing tolerances. "Tufted Yarn Weight" refers to total input weight of yarn used in tufting process, and processes such as tufting and shearing will result in a lower finished yarn weight in purchased carpet. Pile Density stated in the Product Specifications is based on the Tufted Yarn Weight. Product Specifications may be changed without notice as long as product performance is not materially affected.