

shaw contract group®

ambition II
20

broadloom specifications

style name	ambition ii 20	
style number	60256	
construction	textured loop	
fiber	olefin	
dye method	100% solution dyed	
	english	metric

pattern repeat	none	
tufted weight	20.0	678.11 g/m ²
gauge	1/10	39.37 per 10cm
stitches per inch	9.0	35.43 per 10cm
finished pile thickness	0.167	4.24 mm
total thickness	0.321	8.15 mm
average density	4311	159.85 kg/m ³
product size	12 foot	3.66 m
primary backing	synthetic	
secondary backing	classcbac®	
protective treatments	ssp® shaw soil protection	

testing

radiant panel	class II
nbs smoke	less than 450
electrostatic propensity	less than 3.5 kv

warranties

10 year commercial limited warranty

installation method

direct glue

coordinating products

environmental certification

green label plus certification number glp 6878



Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice.

shawcontractgroup.com | 1 800.257.7429