

InPro Armorwall Interior Coatings Repair Guide

Although the use of Armorwall 2500 will greatly reduce the need for repainting and offers uncommon hide characteristics and stain resistance - it may occasionally get damaged and need repair. Because of the eggshell sheen it may require special care to ensure a successful repair.

First: Surface Repair

If the substrate is damaged it must be repaired to the same level of smoothness as the original installation prior to continuing. Variations in the surface will reflect differently and result in a visual blemish.

Second: Priming

Porous surfaces can lead to touch-up issues in both color and sheen. Make sure all repairs start with the correct primer for the substrate. This can cause problems if the original substrate was not primed prior to application because then any touch-up will show up with a different sheen.

Third: Finish Coat Application

If available, use Armorwall product from the original installation. Use the same method of application as used in the original application. For example, if sprayed, repair should be sprayed. If Brushed, repair should be brush applied.

NOTE: Brushing a repair over a finish that was rolled will leave a noticeable difference in finish appearance.

NOTE: Avoid build up of Armorwall around touch-up. Lightly feather the material away from the repair.

IPC.633/Rev.1



P.O. Box 406 · Muskego, Wisconsin 53150 USA
inprocorp.com
Nationwide 800.222.5556/Fax 888.715.8407
International Sales 262.679.5521/Fax 262.679.5524

INPRO
IPC Interior Protection Products
and Decorative Surfaces