Test Number: 254304

Independent / Textile

P.O. Box 1948

1503 Murray Ave.

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: ittslab@dalton.net

TEST REPORT

Customer: Masland Carpets, Inc.

July 29, 2005

Subject: Specimens of the submitted sample were prepared and tested in accordance with the procedures proposed by the National Institute of Standards and Technology (formerly National Bureau of Standards), Technical Note 708 and NFPA 258, ASTM E 662-03.

SMOKE DENSITY TEST (NIST)

Operating Conditions

Irradiance:

2.5 watts/cm²

G Factor

132

Thermal Exposure:

Non-flaming

Furnace Voltage:

107

Burner Fuel:

Sample Description

Style: 7245 Curtain Wall

Test Results

Chamber Temperature, °F (start)

Chamber Pressure

Minimum Transmittance (TM), %

at, minutes

Maximum Specific Optical Density (DM)

Clear Beam, (DC)

DM, CORRECTED (DMC)

Specific Optical Density at 1.5 minutes

Specific Optical Density at 4.0 minutes

Time to 90% DM, minutes

Time to DS = 16, minutes

	#1	#2	#3	Average
	95	95	95	
1	Mair	tained positi		' H₂O
		1		1

93%	81%	23%			
20.00	19.60	20.00	19.90		
136	144	216	165		
2	2	1	2		
134	142	215	164		
1	1	1	1		
29	25	27	27		
16.00	16.70	17.70	16.80		
2.90	2.70	3.00	2.90		

L. Kent Suddeth

Executive Vice President