TEST REPORT

DATE: 03/04/2010	TEST NUMBER: 127044
------------------	---------------------

TEST METHOD CONDUCTED	AATCC 134-06 (Step Me	ethod) Electrostatic Propensity of Carpets
-----------------------	-----------------------	--

DESCRIPTION OF TEST SAMPLE				
IDENTIFICATION	T432 Particle			
COLOR	04422			
ROLL	1000032781			
CONSTRUCTION	Loop Pattern			
FIBER	Antron ® Legacy Nylon			
BACKING	Vinyl			
REFERENCE				

GENERAL PRINCIPLE

This method is designed to assess the static propensity of flooring material by controlled laboratory simulation of conditions which are known from experience to be strongly contributory to excessive accumulation of static charges.

A flooring material preconditioned to equilibrium at controlled atmospheric conditions is walked on by a test subject in a specified manner with specified shoe soles. The static charges which build up on the tester are monitored continuously by a recorder.

A neolite shoe sole has been chosen as the primary reference material because its static performance is much like that of many common leathers. It is a commonly used shoe sole material and can be easily cleaned, while its chemical and physical properties are quite uniform.

A chrome tanned leather shoe sole has been chosen for a secondary reference material because it is representative of a certain class of leathers whose performance differs significantly from that of neolite soles on certain carpet fiber. Statistically, chrome tanned leather comprises a very small percentage of the shoe sole market, but must be considered in critical applications.

TEST CONDITIONS				
TEST CONDITIONS The sample is conditioned to equilibrium and tested at 70 ° ± 2° F and 20 ± 2% relative				
	humidity			
SAMPLE PREPARATION	Shampooed three times according to GSA specifications			
SUBSTRATE	Tested Over Grounded Metal Plate			

	DAY 1	DAY 2	AVERAGE
TEST I: Step Test/Neolite Sole	-0.5 KV	-0.3 KV	-0.4 KV
TEST III: Step Test/Leather Sole	+0.5 KV	+0.4 KV	+0.5 KV
MAXIMUM AVE	MAXIMUM AVERAGE VOLTAGE		KV

"The results of this test relate to the sample of flooring material tested. Its static performance may be altered in service as a result of wear, soiling, cleaning, temperature, relative humidity, etc..."

APPROVED BY:

Lang atluny

NV(AÅ

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us