

## **TEST REPORT**

**DATE: 10/28/2009 TEST NUMBER**: 124430

CLIENT	Masland Carpets
--------	-----------------

TEST METHOD CONDUCTED	AATCC 16-03 Colorfastness to Light
-----------------------	------------------------------------

DESCRIPTION OF TEST SAMPLE			
IDENTIFICATION	T440 Solar		
COLOR	04133 Altair		
ROLL			
CONSTRUCTION	Loop Pile		
FIBER	Antron Lumena® Solution Dyed Nylon		
BACKING	Vinyl		
REFERENCE	GSA INITIAL GSA SIN #31-303		

## **GENERAL PRINCIPLE**

This test specimen is exposed to a predetermined amount of radiant energy under specified conditions of temperature and relative humidity. The lightfastness of the specimen is assessed by comparing the exposed and the unexposed portions of the test sample with the AATCC Gray Scale for Evaluating Color Change.

## **TEST RESULTS**

EXPOSURE	40 AFU
----------	--------

COLOR	RATING	COLOR	RATING	COLOR	RATING
04133 Altair	5.0				

AATCC RATING KEY				
5	No change			
4	Slight change			
3	Noticeable change			
2	Considerable change			
1	Severe change			

APPROVED BY:

Lay asluy

KVĮVĎ

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glentwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us