

Arctic 4011

Best In Show 9651

Specifications

Contents

50% recycled solution-dyed nylon
50% solution-dyed nylon

Weight

14.9 ± 1.0 oz./lin. yd.

Width

54" min. useable

Repeat


1.1" vertical, 1.2" horizontal

Treatment

BLOCKaide™

Backing

acrylic



Cleaning Code

Standard Care Label W-S.

Clean with water based cleaning agents, foam or pure, water free solvents.
Vacuuming or light brushing is recommended to prevent dust and soil buildup.

Performance



Breaking Strength (ASTM D5034)

250 lbf min. warp and fill

Tear (ASTM D2261)

20 lbf min. warp and 25 lbf min fill

Seam Slippage (ASTM D4034)

55 lbf min. warp and fill

Pilling resistance (ASTM D3511)

Class 4 min.

Colorfastness to light (AATCC 16 Option 3)

Grade 4 min. at 200 hours

Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

Colorfastness to water (AATCC 107)

Class 3 min. for staining
Class 4 min. for color change

Wyzenbeek Abrasion resistance (ASTM D4157)

145,000 double rubs min. cotton duck

Flammability

CA Tech Bulletin 117 Sec. E
NFPA 260/UFAC Fabric Classification - Class I



Guilford of Maine