

Ivory 010

Route 66 2701

Specifications

Contents

20% post-consumer recycled polyester
50% pre-consumer recycled polyester
30% polypropylene

Weight

13.9 ± 1.0 oz./lin. yd.

Width

66" min. useable

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup.

Performance



Breaking Strength (ASTM D5034)

250 lbf min. warp and 150 lbf min fill

Tear (ASTM D2261)

40 lbf min. warp and 30 lbf min fill

Colorfastness to light (AATCC 16 Option 3)

Grade 4 min. at 40 hours

Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

Flammability

ASTM E84 Class I or A

NRC of anechoic termination

1.00

NRC of fabric in front of anechoic termination

.90



The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

