
















Technical specifications

colorex[®] concept




Colorex Concept meets the requirements of EN 649

	Total thickness	EN 428	2.0 mm
	Collection size		29
	Commercial very heavy	EN 685	34
	Industrial general	EN 685	43
	Tile size	EN 427	610 x 610 mm
	Total weight	EN 430	3.0 kg/m ²
	Dimensional stability	EN 434	0.05 %
	Residual indentation	EN 433	0.035 mm
	Abrasion resistance	EN 660-1	Group P
	Castor chair	EN 425	No effect
	Light fastness	EN 20 105-B02	≥6
	Resistance to chemicals	EN 423	Excellent
	VOC emissions	AgBB / DIBT	Suitable for indoor applications
	Slip resistance	DIN 51130	R9
	Thermal conductivity	EN 12524	0.28 W/(m.K)

Colorex Concept meets the requirements of EN 14041



EN 14041

	Reaction to fire	EN 13501-1	B _{fl} - s1
	Slip resistance	EN 13893	DS - μ > 0.50
	Static electrical propensity	EN 1815	< 2 kV

The above information is subject to modifications for the benefit of further improvements