

DESCRIPTION

Total thickness	ASTM F386-02	inch	0.08
	EN 428	mm	2.00
Wearlayer thickness	ASTM F410-02	inch	0.08
	EN 429	mm	2.00
Weight	-	lbs/sq.ft.	0.62
	EN 430	g/sq.m	3040
Width	-	feet - inch	6'6"
	EN 426	cm	200
Length	-	feet - inch	66'
	EN 426	m	20
Coverage / roll	-	sq.ft.	430.56
	-	sq.m	40

CLASSIFICATION

Reference specification	ASTM F1913-04	-	compliant
Fire rating	ASTM E648-08	class	Class I
	CAN/ULC S102.2	-	tested in accordance

PERFORMANCES

Bacteriostatic & fungistatic	-	-	OK
Surface treatment / maintenance	-	-	PUR Protect®
Abrasion	ASTM F510-04	mg	3.5
Wear resistance	EN 660.2	mm ³	≤ 4.0
Coefficient of friction	ASTM D2047-04	-	0.98
	ASTM C1028-96		0.67
Static load (250 psi)	ASTM F970-00	inch	-0.002
Dimensional stability	-	-	Excellent
Impact insulation class	ASTM E989-06	-	42
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Chemical & stain resistance	ASTM F925-02	-	Excellent Test results available upon request

ENVIRONMENT

Certification	-	-	Floorscore™
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10