

Alabaster 9010

Aurora 2961

Specifications

Contents

38% post-consumer recycled polyester
62% FR polyester

Weight

17.2 ± 1.0 oz./lin. yd.

Width

72" min. useable

Repeat

6.6" vertical, 18.8" horizontal

Treatment

FR antimicrobial

Cleaning Code

Standard Care Label W-S. Commercial wash at 160°F maximum wash temperature using detergents recommended for the type of washing machines being used, no chlorine bleach. Rinse warm. Do not overload the washer as this may result in inadequate cleansing of the fabric and excessive wrinkling. Dry on synthetic (cool) setting until slightly damp or just dry. Do not overload the dryer. Over-drying or drying at hot temperatures may cause unacceptable shrinkage to occur. If necessary, press with a cool iron ("polyester" or "synthetics" setting, max temp 275° F).

Performance



Breaking Strength (ASTM D5034)

150 lbf min. min. warp and 175 lbf min. min fill

Tear (ASTM D2261)

10 lbf min. min. warp and 20 lbf min. min fill

Seam Slippage (ASTM D4034)

60 lbf min. warp and 50 lbf min. fill

Colorfastness to light (AATCC 16 Option 3)

Grade 4 min. at 60 hours

Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

Flammability

NFPA 701 TM#1 Pass

