

SPECIFICATIONS  
FOR UPHOLSTERY

## SPECIFICATIONS

|               |                                                             |
|---------------|-------------------------------------------------------------|
| Style         | Basketweave, Mini Basketweave:                              |
| Fiber Content | 70% vinyl, 30% polyester                                    |
| Width         | 72" wide (1.83 meters)                                      |
| Weight        | 24 oz/sy (0.82 kilograms/m2) *Weights vary by weave         |
| Style         | Bamboo:                                                     |
| Fiber Content | 70% vinyl, 30% polyester                                    |
| Width         | 72" wide (1.83 meters)                                      |
| Weight        | 15-18 oz/sy (0.36-0.42 kilograms/m2) *Weights vary by weave |

## FLAMMABILITY TESTS

| TEST CONDUCTED       | DESCRIPTION  | INDUSTRY STANDARD          | RESULTS                  |
|----------------------|--------------|----------------------------|--------------------------|
| California 117E      | Flammability | Burning Time: <3.5 seconds | Complies Burning Time: 0 |
| ASTM E84 (Adhered)   | Flammability | Class A                    | Class A                  |
| ASTM E84 (Unadhered) | Flammability | Class A                    | Class A                  |
| UFAC                 | Flammability | Class 1                    | Class 1                  |

## CROCKING TESTS

| TEST CONDUCTED | DESCRIPTION      | INDUSTRY STANDARD                    | RESULTS              |
|----------------|------------------|--------------------------------------|----------------------|
| AATCC 8        | Wet/Dry Crocking | Grade 4 min. Dry<br>Grade 3 min. Wet | Complies<br>Complies |

## PHYSICAL PROPERTIES TESTS

| TEST CONDUCTED  | DESCRIPTION       | INDUSTRY STANDARD      | RESULTS            |
|-----------------|-------------------|------------------------|--------------------|
| AATCC 16-3      | Lightfastness     | Grade 4 @ 40 hours     | Grade 5 @ 40 hours |
| ASTM D3511      | Brush Pill        | Class 3 min.           | Class 5            |
| ASTM D5034      | Breaking Strength | Class A                | Class A            |
| ASTM D434/D3597 | Seam Slippage     | 25 lbs. min. Warp/Fill | Complies           |
| ASTM 4034       | Seam Slippage     | 25 lbs. min. Warp/Fill | Complies           |

## RESISTANCE TESTS

| TEST CONDUCTED | DESCRIPTION            | INDUSTRY STANDARD | RESULTS     |
|----------------|------------------------|-------------------|-------------|
| ASTM G21       | Resistance to Fungi    | No Standard       | Zero Growth |
| ASTM G22       | Resistance to Bacteria | No Standard       | Zero Growth |

## SPECIFICATIONS FOR UPHOLSTERY

### WIDTH TESTS

| TEST CONDUCTED | DESCRIPTION | INDUSTRY STANDARD | RESULTS |
|----------------|-------------|-------------------|---------|
| 72"            |             |                   |         |

### WEIGHT TESTS

| TEST CONDUCTED                    | DESCRIPTION              | INDUSTRY STANDARD | RESULTS |
|-----------------------------------|--------------------------|-------------------|---------|
| Basketweave,<br>Mini Basketweave: | 23.1 oz per square yard  |                   |         |
| Bamboo:                           | 15-18 oz per square yard |                   |         |