



## Textile Testing

553 76<sup>th</sup> Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119



TESTING CERT. #3193.01

Report Number: 55917

Date: 12-14-2012

For the Account Of: Sina Pearson Textiles  
150 Varick Street  
New York, NY 10013  
Contact: Sina Pearson

Client's Identification: Alhambra 401 with Nano-tex®, VC1 and Acrylic Backing

**Test Performed** California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 – CS 191-53) Upholstery Fabrics, March 2000

### TEST DATA

☒ Plain Surface

☐ Raised Surface

Specimen	Flame Spread	Flame Spread
	<b>Warp Face</b> (seconds)	<b>Warp Back</b> (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

Specimen	Flame Spread	Flame Spread
	<b>Fill Face</b> (seconds)	<b>Fill Back</b> (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

### ABBREVIATIONS USED

**DNI** Did not ignite when exposed to test ignition source  
**IBE** Ignited but extinguished before burning through stop cord  
**SF** Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric  
**TSF** Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric

### ACCEPTANCE CRITERIA

- With nap** - Minimum flame spread of any individual specimens shall be 7 seconds. (ACT Criteria decreases minimum time to 4 seconds)
- Without nap** - Minimum flame spread of any individual specimens shall be 3.5 seconds.

**CONCLUSION** Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies  
☐ Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

*C. Venturini*

Authorized Signature-MB