Spinneybeck

Technical Data Sheet

Capri (CP)

| Uphoistery | Leather | lechnical | Data |
|------------|---------|-----------|------|
| | | | |

Leather Specifications

Style Capri (CP)

Description Full grain, aniline dyed

Thickness 1.2–1.4 mm

Weight 3.0–3.5 oz. per sq. ft.

Average Hide Size 55–60 sq. ft.

Finish: Breathable, light, protective finish

Performance Characteristics Tests

Light Fastness (AATCC Method 16, Option E, 72 Hours) Class 4

Crocking (ASTM D5053) Dry: Class 4 Wet: Class 3

Abrasion (ASTM D7255) 300+ cycles (CS-10 wheels)

Flex (ASTM D2097) 70,000 flexes

Tearing Strength, Double Hole (ASTM D4705) 25 lbs.

Breaking Force (ASTM D2208) 200 lbs.

Elongation (ASTM D2211) 30-50% at 50 lbs.

Flammability Passes the following flammability tests

California Technical Bulletin 117 Complies

Boston Fire Dept. BFD IX-1 Complies (with flame treatment)

Surface Burning Characteristics of Bldg. Materials (ASTM E84) Class I with flame treatment

*Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent.

Recommended Cleaning Instructions

Dust regularly. Minor spots can be washed off using lukewarm water and mild soap.

Do not soak. Never clean with abrasive solvents, alcohol, or wax-based products.

Approved maintenance products are available from Spinneybeck.