## Spinneybeck Technical Data Sheet

## Cervo (CV)

Upholstery Leather	Technical Data
Leather Specifications	
Style	Cervo (CV)
Description	Full grain, aniline dyed leather GREENGUARD Certfied
Thickness	1.4–1.6 mm
Weight	3.5–4.0 oz. per sq. ft.
Average Hide Size	50–55 sq. ft.
Finish	Naked
Performance Characteristics	Tests
Light Fastness (AATCC Method 16, Option E, 72 Hours)	Class 3
Crocking (ASTM D5053)	Dry: Class 4
Abrasion (ASTM D7255)	N/A
Flex (ASTM D2097)	N/A
Tearing Strength, Double Hole (ASTM D4705)	50 lbs.
Breaking Force (ASTM D2208)	500 lbs.
Elongation (ASTM D2211)	30–50% at 50 lbs.
Flammability	Passes the following flammability tests
California Technical Bulletin 117	Complies
Surface Burning Characteristics of Bldg. Materials (ASTM E84)	Class I with flame treatment
*Successfully used in CAL 133 applications with Fireg	ard F187 fire backer material or equivalent.

## **Recommended Cleaning Instructions**

Dust regularly. Minor spots can be washed off using lukewarm water and mild soap. Do not soak. Never clean with abrasive solvents, alcohol, or wax-based products. Approved maintenance products are available from Spinneybeck.