

Upholstery Leather

Technical Data

Leather Specifications

Style	Copenhagen (CO)
Description	Full grain, aniline dyed, naked leather GREENGUARD Certified
Thickness	1.1–1.2 mm
Weight	2.75–3.00 oz. per sq. ft.
Average Hide Size	45–50 sq. ft.
Finish	Naked

Performance Characteristics

Tests

Light Fastness (AATCC Method 16, Option E, 72 Hours)	Class 2-3
Crocking (ASTM D5053)	Dry: Class 2-3
Abrasion (ASTM D7255)	N/A
Flex (ASTM D2097)	N/A
Tearing Strength, Double Hole (ASTM D4705)	25 lbs.
Breaking Force (ASTM D2208)	200 lbs.
Elongation (ASTM D2211)	30–50% at 50 lbs.

Flammability

Passes the following flammability tests

California Technical Bulletin 117	Complies
Surface Burning Characteristics of Bldg. Materials (ASTM E84)	Class I with flame treatment

*Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent.

Recommended Cleaning Instructions

Dust regularly. Minor spots can be washed off using lukewarm water and mild soap.

Do not soak. Never clean with abrasive solvents, alcohol, or wax-based products.

Approved maintenance products are available from Spinneybeck.