

Upholstery Leather Technical Data

Leather Specifications

Style	Distressed (DT)
Description	Full grain, aniline dyed leather GREENGUARD Certified
Thickness	1.1–1.3 mm
Weight	2.75–3.25 oz. per sq. ft.
Average Hide Size	55–60 sq. ft.
Finish	Breathable protective finish

Performance Characteristics

Tests

Light Fastness (AATCC Method 16, Option E, 72 Hours)	Class 2–3
Crocking (ASTM D5053)	Dry: Class 2–3
Abrasion (ASTM D7255)	N/A
Flex (ASTM D2097)	N/A
Tearing Strength, Double Hole (ASTM D4705)	25 lbs.
Breaking Force (ASTM D2208)	200 lbs.
Elongation (ASTM D2211)	30–50% at 50 lbs.

Recommended Cleaning Instructions

Dust regularly. Minor spots can be washed off using lukewarm water and mild soap.

Do not soak. Never clean with abrasive solvents, alcohol, or wax-based products.

Approved maintenance products are available from Spinneybeck.