

Upholstery Leather

Technical Data

Leather Specifications

Style:	Riva (RA)
Description:	Full grain, aniline dyed, naked leather GREENGUARD certified
Thickness:	1.0–1.1 mm
Weight:	2.50–2.75 oz. per sq. ft.
Average Hide Size:	50–55 sq. ft.
Finish:	Naked (water resistant and soil resistant)

Performance Characteristics

Tests

Light Fastness (AATCC Method 16, Option E, 72 Hours)	Class 2-3
Crocking (ASTM D-5053):	Dry: Class 2-3
Tearing Strength, Double Hole (ASTM D-4705):	25 lbs.
Breaking Force (ASTM D-2208):	200 lbs.
Elongation (ASTM D-2211):	30-60% at 50 lbs.
Dynamic Water Absorption (ASTM D-6014):	Weight Gain: 0.267 g
Static Water Absorption (ASTM D-1815):	Weight Gain: 2 hrs. – 1.14 (g) 24 hrs. – 1.93 (g)
Static Water Absorption (ASTM D-1815):	Water Absorption: 2 hrs. – 0.22 (g/cm ³) 24 hrs. – 0.37 (g/cm ³)

Flammability

Passes the following flammability tests

California Technical Bulletin 117	Complies
Surface Burning Characteristics of Bldg. Materials (ASTM E84)	Class II

*Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent.

Water Repellency Tests**AATCC Test Method 130**

Stain Release; Spot Clean Method

Blood, Urine, Bleach	Immediate Grade 4.5; 24 Hr Grade 5.0
Betadine (bleach cleaning)	Immediate Grade 3.5-4.0; 24 Hr Grade 2.5-3.0

Recommended Cleaning Instructions

Dust regularly. Minor spots can be washed off using lukewarm water and mild soap.

Do not soak. Never clean with abrasive solvents, alcohol, or wax-based products.

Approved maintenance products are available from Spinneybeck.