

specifications

style name	whisper
style number	60751
construction	needlebond
pattern	single rib
fiber	50% olefin / 50% PET polyester
dye method	100% solution dyed
secondary backing	SBR latex
total weight	30 oz/ly.
roll size	54" X 24" lin. yd.
packaging	"crush-proof" box

testing

flammability	Passes Corner Burn NFPA-265: UBC 8-2 Tunnel Test, Class A Rating ASTM E-84	
acoustical	ASTM C-423-84A Gypsum Board NRC .20 Acoustic Board NRC .80	
tensile strength	ASTM D-5034, (LBS) Break Elongation L x W L x W 142 x 132 195 x 145	
tear (trap) strength	ASTM D-2261, (LBS) L x W 30 x 25	
abrasion resistance	ASTM D-3884 Rib Rupture # Cycles # Cycles 1,720 2,260	
colorfast	AATCC-168 Wet Crocking Dry Crocking 5 5	
fmvss 302	Passes	
electrostatic	AATCC-134 0.2kv	

warranty

one year limited warranty



Specifications are subject to nominal manufacturing variances.
 Material supply and/or manufacturing processes may necessitate changes without notice.