





ECO-TERR™ TILES

ECO-TERR™ TILES


— standard —




Portifirio Red




Red Ash




Emperador Brown




Solare Yellow




Oyster White



Moor Green




Misty Grey




Carmel Clay




Coco Cream




Bulgari Black




Baby Blue



Cote d' Azure




Ocean Gem




Safari Green




Venetian Beach




Fontana White




Periwinkle




Olympia Blue




Aztec Yellow



Hillcrest Grey




Zuma Beach



Diamante



Evergreen



Silverado Black


— special order —




Platina White




White Gem




Oyster White
w/ Turquoise




Aqua White




Ivory Seashell




Cinnamon Cream




Crema di Parma




Bliss Blue




Ming Red



Rosetta




Forest Gem



Tahitian Cream




Barbados Yellow




Celtic Blue



Morrocan Red



Venetian Brown



Cayman Green

CONTENTS

Up to 80% post industrial
recycled content.

Up to 10% post
consumer recycled content.

FEATURES

Non toxic
Rectified and Calibrated
Mold and Mildew resistant
Contributes to LEED
MR 4.1 and 4.2

APPLICATIONS

Industrial, Residential and
Commercial
Interior and Exterior
Flooring and Worktops

AVAILABLE FINISHES

Polished
Honed (*special order*)
Antique (*special order*)
Sandblasted (*special order*)

AVAILABLE SIZES

16"x16"x5/8"
24"x24"x3/4"

TEST PERFORMED	ASTM	RESULTS
Friction Coefficient	C-1028	Polished Honed Sandblasted Dry:0.64; Wet:0.61 Dry:0.71; Wet:0.68 Dry:0.74; Wet:0.70
Resistance to Fire		Class 0
Freeze-thaw	C-666	None (300 cycles)
Compressive strength	C-170	14,000 -24,000 psi
Modulus of rupture	C-99	1,550 psi
Flexural strength	C-880	1,973 psi
Water absorption	C-97	3.2%

*Approximate average laboratory test values.

*Colors may not display accurately in print materials. Please request sample.



COVERINGS^{ETC}

coveringsetc.com | 800 720 7814