

### Description

A premium waterbased pigmented PVA sealer for interior use on drywall. Seals the substrate providing a good foundation for acrylic topcoats.

### Recommended Uses

New interior drywall and plaster.

### Colors

White

### Packaging

One and five gallon containers

### Surface Preparation

Surfaces must be clean, dry and free from all contaminants & residual dust that may impair adhesion. Not recommended for use over previously painted surfaces.

### Application

Brush, roll or spray. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Clean tools and equipment with soap and water.

### Drying Time

Touch: 30 minutes  
Recoat: 2 hours

### Coverage

250 – 375 square feet per gallon, depending on surface.

### Mil Thickness

Wet = 4.2      Dry = 1.3

### Thinning

Use at package consistency. If thinning is required, use water sparingly.

### Composition

Titanium Dioxide	9.6%
Extenders	13.6%
<b>TOTAL PIGMENT</b>	<b>23.2%</b>
Resin	17.7%
Additives	4.0%
Water	55.1%
<b>TOTAL VEHICLE</b>	<b>76.8%</b>

### Weights & Measurements +/-3.0%

Solids by Volume:	31.0%
Solids by Weight:	41.9%
VOC:	47 g/l
Weight Per Gal:	10.1 lbs.
Viscosity:	90 - 94 KU

### Conformance

**SCAQMD** - complies with Rule 1113, Architectural Coatings

**LEED** - complies with LEED 2009  
-Low Emitting Materials

**DISCLAIMER:** To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.

Revised 09.15