

Metal Pro Primer 4800

Interior/Exterior Acrylic Metal Primer

Architectural Coating - Premium Plus

## **Description**

Metal Pro Primer is a premium plus, low VOC, fast drying, waterborne, acrylic coating for interior and exterior use. This product offers excellent adhesion to metal surfaces particularly galvanized metal; hence protecting the metal surface from oxidation. This product can be top coated with a variety of products, but for the best protection of metal surfaces top coat Metal Pro with Protec Alkyd Emulsion Enamels (9700 Satin, 9800 Semi-Gloss or 9900 Gloss).

## Recommended Uses

Metal Pro is recommended for non-ferrous metal (not containing iron) and galvanized metals. For best corrosion resistance on ferrous metals use 9600 Protec Metal Prime.

## Colors

White (4800), Black (4805), Red Oxide (4810) and custom colors.

# <u>Packaging</u>

One and five gallon containers and 55 gallon drums

#### <u>Finish</u>

Flat angular sheen @ 85° = 8.0%

# Surface Preparation

**New Surfaces:** remove all loose dirt, oil, grease, wax or other contaminants from the surface. To ensure proper adhesion all new galvanized metal must be acid etched using a product such as Jasco Prep N' Prime, distributed by Vista Paint Corporation. Remove the residue after etching.

Previously Coated Surfaces: remove all loose paint, grease, dirt or other contaminants before application of primer.

## <u>Application</u>

Brush or spray. Mix thoroughly. Apply only when air and surface temperatures are between 55°F - 100°F, and the relative humidity is no greater than 80%.

**Caution:** Extreme high or low humidity may have an effect on both dry time and finishes.

# **Drying Time**

Tack Free: 30 - 60 minutes
Handling: 1.0 - 1.5 hours
Recoat: 1.5 - 2.0 hours
Moisture Resistance: 12 hours

**Drying Schedule:** Dry times are based on 70° F @ 80% relative humidity. Dry times will be extended at increased humidity above 80° F and temperatures below 50° F.

# Coverage

430 square feet per gallon at 1.5 mils. Overall coverage will depend on method of application and surface conditions of substrates.

# Suggested Mil Thickness

Wet: 4 - 7 mils per coat
Dry: 1.2 - 2.5 mils per coat

# **Thinning**

If thinning is required per specific applications, thin only with clean water sparingly.

## Clean Up

Flush spray lines immediately with water. Wash tools promptly with clean soap and water.

Next Page

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.

Revised 01.16



Metal Pro Primer

Interior/Exterior Acrylic Metal Primer

Architectural Coating - Premium Plus

Continued

#### Recommended Finish Coat

Protec Alkyd Emulsion Enamels (9700 Satin, 9800 Semi-Gloss or 9900 Gloss). Other topcoats may be suitable for use if maximum corrosion resistance is not required.

# Product Mixing

Important! Agitate or stir before using product to allow for uniform consistencies of product.

# Equipment

Conventional / airless spray equipment. Tip sizes may vary depending on type of equipment used and manufacturer specs. It is recommended a small test strip be sampled in an inconspicuous area for desired application requirements.

#### Conventional Spray:

Atomization Pressure 25-60 psi Fluid Pressure 20-40 psi Air Nozzle 66 SD Fluid Nozzle 25 psi

Airless Spray

 Pressures
 2000 psi

 Tips
 0.13" – 0.19"

 Hose
 ¼" ID

 Filter
 60 mesh

Brush / Roller Nylon, 1/4" - 1/2" Nap

## Composition

Titanium Dioxide 10.6% Extenders 20.4% TOTAL PIGMENT 31.0%

Acrylic Resin 19.3% Additives / Solvents 9.0% Water 40.7% TOTAL VEHICLE 69.0%

Weights & Measurements +/-3.0%

Solids by Volume: 37.0% Solids by Weight: 52.2% VOC: 49 g/l Weight Per Gal: 11.1 lbs. Viscosity: 77 KU

#### **Testing**

Adhesion (ASTM D 3359-97) 10
Prohesion (ASTM D 5894-96) 10
1000 Hours

Humidity Resistance (ASTM D 4587-91) 10 500 Hours

## Conformance

SCAQMD - complies with Rule 1113, Architectural Coatings

**LEED** - complies with LEED 2009 and LEEDv4 -Low Emitting Materials

CDPH Section 01350 - tested and passed MPI - #107, #134

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.