

### Interior Alkyd Emulsion Enamel Finish

Architectural Coating - Premium Plus

#### Description

Aqua Fusion is a premium plus waterborne interior alkyd emulsion enamel with superior gloss, brush-ability and spray-ability achieved by using breakthrough technology in coating chemistry. This is an environmentally preferable product with low odor and low VOC. The application characteristics are equal to or better than "old alkyd enamel" with an alkyd-like hardness, print resistance and better yellowing resistance than conventional alkyd products. Cleans up with water instead of solvent.

#### Recommended Uses

For use on interior drywall, concrete, wood and primed metal surfaces that require hard and glossy enamel. This product can also be used for exterior doors and frames.

#### Colors

White and special order factory tint.

#### Packaging

One and five gallon containers

#### Finish

Gloss, sheen @ 60° = 88.92%

#### Surface Preparation

Surfaces must be clean, dry and free from all contaminants that may impair adhesion. Sand to smooth finish and remove sanding dust. For maximum adhesion, scuff sand all slick or glossy surfaces. May be applied over previously painted latex or oil surfaces with proper preparation.

#### Primer

Drywall:	6600 AquaLac
Concrete/Wood:	6600 AquaLac
Ferrous Metal:	9600 Protec Metal Prime White
	9610 Protec Metal Prime Red Oxide
Non-Ferrous Metal:	4800 Metal Pro Primer White
	4810 Metal Pro Primer Red Oxide

#### Application

Brush, roll or spray. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Clean tools and equipment with soap and water.

#### Drying Time

Touch:	2 hours
Recoat:	6 hours

#### Coverage

350 – 400 square feet per gallon.

#### Mil Thickness

Wet = 6.0 - 8.0	Dry = 2.0 - 3.0
-----------------	-----------------

#### Thinning

Use water sparingly.

#### Composition

Titanium Dioxide	23.7%
Extenders	4.5%
<b>TOTAL PIGMENT</b>	<b>28.2%</b>
Proprietary Resin	25.2%
Additives / Solvents	3.0%
Water	43.6%
<b>TOTAL VEHICLE</b>	<b>71.8%</b>

Weights & Measurements +/-3.0%

Solids by Volume:	40.3%
Solids by Weight:	55.0%
VOC:	4 g/l
Weight Per Gal:	11.0 lbs.
Viscosity:	94 - 98 KU

#### Conformance

**SCAQMD** - complies with Rule 1113, Architectural Coatings

**LEED** - complies with LEED 2009  
-Low Emitting Materials

**DISCLAIMER:** To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.

Revised 03.15