



Dry Fall Flat DF12

DF12 Dry Fall Flat Interior Acrylic Water-based Flat Finish

Interior Acrylic Water-based Flat Finish

Architectural Coating - Premium

Description

A premium water-based acrylic flat dry fall designed for commercial ceilings. Overspray dries to powder after falling approximately 12 feet. Dry Fall properties will depend on an ambient temperature and humidity.

FOR PROFESSIONAL OR CONTRACTOR USE ONLY.

Recommended Uses

Industrial and commercial ceilings where good hide and adhesion are required.

Colors

White, pastel and deep colors.

Packaging

Five gallon containers

Finish

Flat, sheen @ 85° = 2.0%

Surface Preparation

All contaminants that may impair adhesion should be removed. Glossy or slick surfaces must be scuff sanded and may require priming.

Primer

Concrete:	4600 Uniprime II
Wood:	4200 Terminator II
Ferrous Metal:	9600 Protec Metal Prime White
	9610 Protec Metal Prime Red Oxide
Non-Ferrous Metal:	4800 Metal Pro Primer White
	4810 Metal Pro Primer Red Oxide

Application

Spray only. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Clean tools and equipment with soap and water.

Drying Time

Touch: 15 - 20 minutes

Coverage

300 - 350 square feet per gallon, depending on surface.

Mil Thickness

Wet = 4.4 Dry = 1.5

Thinning

DO NOT THIN.

Composition

Titanium Dioxide	6.7%
Extenders	27.9%
TOTAL PIGMENT	34.6%

Acrylic Resin	10.0%
Additives / Solvents	6.5%
Water	48.9%
TOTAL VEHICLE	65.4%

Weights & Measurements +/-3.0%

Solids by Volume:	41.7%
Solids by Weight:	61.0%
VOC:	18 g/l
Weight Per Gal:	11.6 lbs.
Viscosity:	90 - 94 KU

Conformance

SCAQMD - complies with Rule 1113, Architectural Coatings

LEED - complies with LEED 2009

-Low Emitting Materials

MPI - #118

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.

Revised 01.16