

TC60

Interior Clear Water-based Semi-Gloss Lacquer

Industrial Coating - Specialty

Description

A water-based clear semi-gloss lacquer, designed for interior applications on cabinets, furniture, paneling and other wood substrates.

Drying Time

Fouch: 20 -25 minutes, force dried @

Recommended Uses

Wood primed with sanding sealer.

Coverage

400 square feet per gallon, depending on surface.

<u>Colors</u>

Clear

Mil Thickness

Vet = 4.0 Dry = 1

<u>Packaging</u>

Five gallon containers and 55 gallon drums

Thinning

<u>Finish</u>

Semi-Gloss, sheen @ 60° = 55.0%

<u>Composition</u>

Clay / Silica 0.09%
Acrylic Resin 28.0%
Additives / Solvents 19.0%
Water 53.0%
TOTAL VEHICLE 100.0%

Surface Preparation

All contaminants that may impair adhesion should be removed. TC10 Sanding Sealer must be applied as first coat to minimize grain raise of wood and provide excellent clarity with grain definition.

Weights & Measurements +/-3.0%

Solids by Volume: 30.0% Solids by Weight: 32.0% VOC: 228 g/l Weight Per Gal: 8.4 lbs.

Viscosity: 40 - 50 Sec Zahn #2 Cup

<u>Primer</u>

Mood.

TC10 Sanding Sealer

Application

Spray only. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Clean tools and equipment with soap and water.

Conformance

SCAQMD - complies with Rule 1113, Architectural Coatings

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties or fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.

Revised 03.1