



**Product Specifications Sheet** 



## Deco Screen 3%

### **Specifications**

**Product Category:** Conventional Composition: 36% Fiberglass / 64% Vinyl

**Openness Factor: Standard Packaging:** Rolls of 30 ly (27 lm)

98" (250 cm) **UV Blockage:** Approximately 97% Width: Weight: **Fabric Style:** Rib Weave 12.21 oz / yd2 (414 g / m2) ± 5%

8553 Thickness: .023" (0.58 mm) ± 5% Item #:

#### **Glass Performance**

Glass : Ci ioi illanec										
Glass Type	Appearance	VLT (Tv)	SHGC (G-Value)							
Common Glass Types	Clear	70	0.38							

Common Glass Types: Guardian SN68, Viracon 1-2 M, PPG Solarban 60

Coating and Location: Low E on Surface #2 Construction: 6 mm / 1/2" air / 6 mm

#### **Fabric Performance**

# Fabric + Glass Performance

Color#	Color Name	Ts	Rs	As	VLT (Tv)	SHGC (G-Value) Interior Fabric	% Improvement of SHGC with Fabric
D012	Parchment	16	64	20	12	0.29	24%
D112	Naturelle	13	54	33	9	0.30	21%
D137	River Rock	7	33	60	6	0.33	13%
D212	Tumbleweed	8	30	62	6	0.33	13%
D226	Harvest	6	15	79	5	0.36	5%
D237	Hazelnut	4	13	83	4	0.36	5%
D249	Flagstone	6	23	71	5	0.34	11%

The performance tests were conducted in accordance with EN 14501:2005, ASTM E891, ASTM E903-96; Solar Heat Gain Coefficient SHGC (G-Value), Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Light Transmission VLT (Tv), Double Glazing 6 mm / ½" air / 6 mm with low E on surface #2. Glass performance tests were conducted using the Lawrence Berkeley National Laboratory Window 6.3 NFRC certified software. Acoustical performance tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com

**Fabrication Methods: Fire Classifications: Environmental Benefits:** 

Cutting: cold, ultrasonic or crush NFPA 701-10 TM#1, California U.S. Title 19

RoHS - Lead Free Welding: radio frequency, high frequency, impulse, CAN/ULC-S109-03 Small Flame Test

hot air, wedge

**Bacterial and Fungal Resistance: Acoustical Performance:** 

ASTM E2180, ASTM G21 NRC: 0.35, SAA: 0.33

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

### Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

5970 N. Main Street • Cowpens, SC 29330 Sales Department: Ph (866) 902-9647

info@mermetusa.com

6.15 v1 www.mermetusa.com