



## Deco Screen 5%

### Specifications

<b>Product Category:</b>	Conventional	<b>Composition:</b>	36% Fiberglass / 64% Vinyl
<b>Openness Factor:</b>	5%	<b>Standard Packaging:</b>	Rolls of 30 ly (27 lm)
<b>UV Blockage:</b>	Approximately 95%	<b>Width:</b>	98" (250 cm)
<b>Fabric Style:</b>	Rib Weave	<b>Weight:</b>	11.3 oz / yd2 (385 g / m2) ± 5%
<b>Item #:</b>	8555	<b>Thickness:</b>	.020" (0.52 mm) ± 5%

### Glass Performance

Glass Type	Appearance	VLT (Tv)	SHGC (G-Value)
Common Glass Types	Clear	70	0.38

**Common Glass Types:** Guardian SN68, Viracon 1-2 M, PPG Solarban 60

**Coating and Location:** Low E on Surface #2

**Construction:** 6 mm / 1/2" air / 6 mm

### Fabric Performance

Color#	Color Name	Ts	Rs	As	VLT (Tv)	SHGC (G-Value)	% Improvement of SHGC with Fabric
D012	Parchment	16	63	21	12	0.29	24%
D112	Naturelle	15	52	33	11	0.30	21%
D137	River Rock	10	33	57	9	0.33	13%
D212	Tumbleweed	10	29	61	8	0.34	11%
D226	Harvest	8	16	76	6	0.35	8%
D237	Hazelnut	7	14	79	7	0.36	5%
D249	Flagstone	8	20	72	7	0.35	8%

### Fabric + Glass Performance

The performance tests were conducted in accordance with EN 14501:2005, ASTM E891, ASTM E903-96: Solar Heat Gain Coefficient SHGC (G-Value), Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Light Transmission VLT (Tv), Double Glazing 6 mm / 1/2" air / 6 mm with low E on surface #2. Glass performance tests were conducted using the Lawrence Berkeley National Laboratory Window 6.3 NFRC certified software. Acoustical performance tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: [www.mermetusa.com](http://www.mermetusa.com)

### Fabrication Methods:

Cutting: cold, ultrasonic or crush  
Welding: radio frequency, high frequency, impulse, hot air, wedge

### Fire Classifications:

NFPA 701-10 TM#1, California U.S. Title 19  
CAN/ULC-S109-03 Small Flame Test

### Environmental Benefits:

RoHS - Lead Free

### Bacterial and Fungal Resistance:

ASTM E2180, ASTM G21

### Acoustical Performance:

NRC: 0.10, SAA: 0.12

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

### Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

5970 N. Main Street • Cowpens, SC 29330

Sales Department: Ph (866) 902-9647

[info@mermetusa.com](mailto:info@mermetusa.com)