











S Screen Origins

Approximately 96%

Specifications

UV Blockage:

Product Category: Conventional Composition: 33.6% Fiberglass / 59.6% Vinyl

6.8% Polyester

Openness Factor: 4% Standard Packaging: Rolls of 23 ly (21 lm)

Width: 98" (250 cm), 122" (310 cm)

Fabric Style: Rib Weave Weight: $18.9 \text{ oz / yd2 (642 g/m2)} \pm 5\%$

Item #: 1604 **Thickness:** .037" (0.93 mm) ± 5%

Glass Performance

Glass Type	Appearance	VLT (Tv)	SHGC (G-Value)	
Common Glass Types	Clear	70	0.38	

Common Glass Types: Guardian SN68, Viracon 1-2 M, PPG Solarban 60

Coating and Location: Low E on Surface #2 Construction: 6 mm / 1/2" air / 6 mm

Fabric Performance

Fabric + Glass Performance

Color#	Color Name	Ts	Rs	As	VLT (Tv)	SHGC (G-Value) Interior Fabric	% Improvement of SHGC with Fabric
02.D1	Porcelain	12	59	29	10	0.29	24%
02.D2	Marble	10	48	42	9	0.31	18%
07.C1	Granite	9	31	60	8	0.33	13%
10.C2	Cork	10	35	55	8	0.33	13%
10.N5	Papyrus	11	38	51	9	0.32	16%
20.C1	Jute	11	43	46	9	0.32	16%
30.W2	Carbon	6	13	81	6	0.36	5%
61.N2	Sepia	5	16	79	5	0.35	8%
61.N3	Patina	6	20	74	5	0.35	8%

The performance tests were conducted in accordance with EN 14501:2005, ASTM E891, ASTM E903-96: Solar Heat Gain Coefficient SHGC (G-Value), Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Light Transmission VLT (Tv), Double Glazing 6 mm / ½" air / 6 mm with low E on surface #2. Glass performance tests were conducted using the Lawrence Berkeley National Laboratory Window 6.3 NFRC certified software. Acoustical performance tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com

Fabrication Methods:

Cutting: cold, ultrasonic or crush Welding: radio frequency, high frequency, impulse, hot air, wedge. Railroading (turning width for length) is not recommended. **Fire Classifications:**

NFPA 701-10 TM#1, California U.S. Title 19 CAN/ULC-S109-03 Small Flame Test

Bacterial and Fungal Resistance: ASTM E2180, ASTM G21

Environmental Benefits:

RoHS - Lead Free

Acoustical Performance:

NRC: 0.15, SAA: 0.14

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

5970 N. Main Street • Cowpens, SC 29330 Sales Department: Ph (866) 902-9647

info@mermetusa.com

www.mermetusa.com 6.15 v1