

## **Product Specifications Sheet**









# GreenScreen® Evolve™ 3%

### **Specifications**

**Product Category:** Sustainable

Openness Factor: 3%

**UV Blockage:** Approximately 97%

Fabric Style: Warp Knit

Item #: 3503

**Composition:** 100% Polyester / 67% Recycled Content

Standard Packaging: Rolls of 50 ly (46 lm)

Width: 118" (300 cm)

**Weight:**  $8.41oz / yd2 (285 g / m2) \pm 5\%$ 

**Thickness:** .027" (0.68 mm) ± 5%

#### **Glass Performance**

Glass Type	Appearance	VLT (Tv)	SHGC (G-Value)						
Common Glass Types	Clear	70	0.38						

Common Glass Types: Guardian SN68, Viracon 1-2 M, PPG Solarban 60

Coating and Location: Low E on Surface #2 Construction: 6 mm / 1/2" air / 6 mm

Fabric Performance Fabric + Glass Performance

Color#	Color Name	Ts	Rs	As	VLT (Tv)	SHGC (G-Value) Interior Fabric	% Improvement of SHGC with Fabric
QS19	Rain	21	50	29	13	0.31	18%
QS21	Shadow	19	51	30	12	0.31	18%
QS22	Shale	25	53	22	19	0.30	21%
QS23	Light	29	62	9	28	0.29	24%
QS26	Storm	18	40	42	8	0.32	16%
Q\$35	Haze	26	59	15	23	0.29	24%
QS37	Wind	26	60	14	23	0.29	24%
Q\$38	Natural	28	60	12	26	0.29	24%
QS39	Cloud	28	65	7	28	0.29	24%

The performance tests were conducted in accordance with EN 14501:2005, ASTM E891, ASTM E903-96: Solar Heat Gain Coefficient SHGC (G-Value), Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Light Transmission VLT (Tv), Double Glazing 6 mm / ½" air / 6 mm with low E on surface #2. Glass performance tests were conducted using the Lawrence Berkeley National Laboratory Window 6.3 NFRC certified software. Acoustical performance tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com

**Fabrication Methods:** 

Fire Classifications:
NFPA 701-10 TM#1, California U.S. Title 19

Environmental Benefits: RoHS - Lead Free, PVC Free

Cutting: cold, ultrasonic or crush Welding: radio frequency, high frequency, impulse, hot air, wedge. May require the use of welding tape.

Please contact Mermet for more information about our welding tape product line.

**Bacterial and Fungal Resistance:** 

Acoustical Performance:

ASTM E2180, ASTM G21

NRC: 0.15, SAA: 0.16

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

#### Care & Handling

Regular light dusting with a feather duster is suggested. A hand-held vacuum with low suction may also be used. When vacuuming, avoid pulling or stretching the fabric. Rigorous vacuuming is not recommended since this could distort the fabric. Alternatively, dirt and debris can be blown away using compressed air or a hand-held hair dryer on the cool setting. Alternatively, a dry chemical sponge may also be used for spot cleaning.

5970 N. Main Street • Cowpens, SC 29330 Sales Department: Ph (866) 902-9647

info@mermetusa.com

www.mermetusa.com 2.16 v1