

LINDSTROM

Lindstrom

Broadloom

Construction

Tufted, Tip Shear

Broadloom Width

13'6" (4.11 m)

Pattern Repeat

162" W x None

Yarn Type

Milliken-Certified WearOn® Nylon Type 6 and 6,6

Stain Repel / Stain Resist / Soil Release

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Continuous Dye

Tufted Face Weight

33 oz/yd² (1,119 g/m²)

Tufts*

160/in² (2,478/100 cm²)

Finished Pile Height

0.2" (5.08 mm)

Average Density (Finished)

5,940

Standard Backing

Endura-Loc™

Available with Cushion-Loc™ attached cushion

Nominal Total Thickness

0.28" (7.1 mm)

Nominal Total Weight

69 oz/yd² (2,340 g/m²)

Flammability (Radiant Panel ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or ASTM-E-662)

≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859)

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 40 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV

Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care Service Network

Indoor Air Quality—CRI Green Label Plus™

GLP8064, Carpet Category 1Y

* This product utilizes Milliken's patented, high density tufting process called multiple yarn infusion. Conventional measurements of gauge and stitch rate are inadequate and misleading. Therefore, tufts per square inch are shown to provide accurate specifications.

WARRANTIES

10 Year Face Fiber Wear

10 Year Delamination of Backing

10 Year Antistatic

10 Year Edge Ravel

5 Year Matting and Crushing

10 Year Tuft Bind

Lifetime Staining/Soiling (StainSmart®)

10 Year Colorfastness

Flammability



Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.