

DESCRIPTION Artic-Forum- Fusion-Metallica-Zenium-Brazilia-Costa Rica- Indiana

Total thickness	EN 428	mm	2.00
Thickness of wearlayer	EN 429	mm	1.02/2.00
Weight	EN 430	g/m ²	2550 / 2580 / 2650 / 2620 / 2780 /2580 /2680
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34-43
Fire rating	EN 13 501- 1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: ramp test with oil	DIN 51 130	class	R10

PERFORMANCES

Wear resistance	EN 660-2	mm ₃	< 2.0
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation (exigency)	EN 433	mm	≤ 0.10
Residual indentation (measure)	-	mm	~0.03
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	Protecsol®

CE MARKING

	EN 14041	-	
		-	