

Independent Textile Testing Service, Inc.

Test No: 143916

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: Shaw Contract

April 4, 2014

Subject: Sample(s) of carpet submitted for testing by the customer and identified below:

Sample Identification: Style name: Activity Tile
Style/Inventory #: 5T089
Color: 00001
Roll #: QN00AD-J
Back: EcoWorx
Test #: S-140325-00049

Test Method Conducted AATCC 134-2011 Electrostatic Propensity of Carpets

Purpose and Scope

This test method is designed to assess the static generating propensity of carpets developed when a person walks across them by controlled laboratory simulation of conditions which may be met in practice, and more particularly, with respect to those conditions which are known from experience to be strongly contributory to excessive accumulation of static charges.

Test Conditions:

Chamber Temperature: 70° F.

Chamber Relative Humidity: 20%

Test Results:	Sole	Underlay	Maximum Voltage 1 (kV)	Maximum Voltage 2 (kV)	Averages (kV)
Test I Step Test	Neolite	Plate	Neg. 0.6	Neg. 1.0	Neg. 0.8
Test II Scuff Test	Neolite	Plate	Neg. 0.8	Neg. 1.1	Neg. 1.0
Test III Step Test	Leather	Plate	Neg. 0.7	--	--
Test IV Scuff Test	Leather	Plate	Pos. 0.5	--	--

Soles:

- a) Neolite XS 664
- b) Suede Leather

Underlayment:

- a) Plate: Earth grounded metal plate
- b) H/J: Standard 40 oz./yd2 rubberized Hair/Jute cushion


President L. Kent Suddeth

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: Shaw Contract

April 4, 2014

Subject: Specimens of the submitted sample were prepared and tested in accordance with the procedures proposed by the National Institute of Standards and Technology (formerly National Bureau of Standards), Technical Note 708 and NFPA 258, ASTM E 662-06.

SMOKE DENSITY TEST (NIST)

Operating Conditions

Irradiance: 2.5 watts/cm² G Factor 132
Thermal Exposure: Non-flaming
Furnace Voltage: 106
Burner Fuel: --

Sample Description

Style name: Activity Tile
Style/Inventory #: 5T089
Color: 00001
Roll #: QN00AD-J
Backing Type: EcoWorx
Test #: S-140325-00049

Test Results

Chamber Temperature, °F (start)

#1	#2	#3	Average
95	95	95	

Chamber Pressure

Maintained positive, under 3" H₂O

Minimum Transmittance (TM), %

15%	21%	50%	
20.00	20.00	20.00	20.00
241	221	172	211
2	1	1	1
239	220	171	210
1	1	1	1
20	24	15	20
17.85	15.63	16.73	16.74
3.80	3.68	4.15	3.88

at, minutes

Maximum Specific Optical Density (DM)

Clear Beam, (DC)

DM, CORRECTED (DMC)

Specific Optical Density at 1.5 minutes

Specific Optical Density at 4.0 minutes

Time to 90% DM, minutes

Time to DS = 16, minutes



President L. Kent Suddeth

PO Box 1948 • 1503 East Morris Street • Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: Shaw Contract

April 4, 2014

Subject: Specimens of the submitted sample were prepared and tested in accordance with
ASTM E 648-10 and/or Federal Test Method 372. NFPA 253

FLOORING RADIANT PANEL TEST

Sample Description

Style Name: Activity Tile
Style/Inventory #: 5T089
Color: 00001
Roll #: QN00AD-J
Backing Type: EcoWorx
Test #: S-140325-00049

Test Assembly

Mounted on 6mm FRC Board
(Using Shaw G5000 Adhesive)

Test Results

	<u>Specimen No. 1</u>	<u>Specimen No. 2</u>	<u>Specimen No. 3</u>
Critical Radiant Flux	0.74 watts/cm ²	0.76 watts/cm ²	0.72 watts/cm ²
Total Burn Length	28.0 cm	27.0 cm	29.0 cm
Flame Front Out	17.0 minutes	17.0 minutes	17.0 minutes

Average Critical Radiant Flux

0.74 watts/cm²

Estimated Standard Deviation

0.02 watts/cm²

2.7% coefficient of variation



President L. Kent Suddeth