

SOUND & FURY

Gesture

Modular Tile

Construction

Tufted, Textured Loop

Tile Sizes

50 cm x 50 cm (19.7" x 19.7")

50 cm x 1 m (19.7" x 39.4")

Yarn Type

ECONYL® Solution-Dyed Nylon Type 6

Stain Repel / Stain Resist / Soil Release

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Solution Dyed

Tufted Face Weight

17 oz/yd² (576 g/m²)

Gauge

1/12

Stitches Per Inch

10.2

Tufts

122.4/in² (1,896/100 cm²)

Finished Pile Height

0.14" (3.56 mm)

Finished Pile Thickness

0.07" (1.78 mm)

Average Density (Finished)

8,163

Standard Backing

PVC-Free Underscore™ ES Cushion

Available with TractionBack®

Recycled Content by Total Weight

ES Backing: 47.3% Pre-Consumer,

8.5% Post-Consumer

ESP Backing: 36.6% Pre-Consumer,

19.3% Post-Consumer

Nominal Total Thickness

0.31" (7.9 mm)

Nominal Total Weight

94 oz/yd² (3,184 g/m²)

Flammability (Radiant Panel

ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care

Service Network

Indoor Air Quality—CRI Green Label Plus™

GLP7205, Carpet Category 13X

Recommended Installation Method(s)

Ashlar (preferred), Monolithic,

Quarter-Turn

WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®)

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.