Milliken

MODERN BLISS

Moulage

Modular Tile

Construction

Tufted, Textured Loop

Tile Size

50 cm x 50 cm (19.7" x 19.7")

Yarn Type

Universal Fibers® Silkworks SDN Type 6,6 and 6

Stain Repel / Stain Resist / Soil

Release

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Solution Dyed

Tufted Face Weight

 $42 \text{ oz/yd}^2 (1424 \text{ g/m}^2)$

Gauge

1/12

Stitches Per Inch

9.5

Tufts

114/in² (1,766/100 cm²)

Finished Pile Height

0.22" (5.59 mm)

Finished Pile Thickness

0.18" (4.50 mm)

Average Density (Finished)

?7600

Standard Backing

PVC-Free Comfort Plus® ES Cushion

Available with TractionBack®

Recycled Content by Total Weight

ES Backing: 38.8% Pre-Consumer,

0.0% Post-Consumer

ESP Backing: 30.7% Pre-Consumer,

8.1% Post-Consumer

Nominal Total Thickness

0.44" (11.2 mm)

Nominal Total Weight

 $129.6 \text{ oz/yd}^2 (4,394 \text{ g/m}^2)$

Flammability (Radiant Panel

ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

< 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

 \geq 4.0 Wet or Dry

Static Electricity (AATCC-134) 20%

R.H.,70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care

Service Network

Indoor Air Quality—CRI Green Label

Plus™

GLP7205, Carpet Category 13X

Recommended Installation Method(s)

Monolithic, Ashlar

WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®) Lifetime Face Fiber Wear Lifetime Antistatic Lifetime Floor Compatibility Lifetime Color Pattern Permanency Lifetime Floor Release
Lifetime Cushion Resiliency
Lifetime Moisture Resistance
Lifetime Delamination of Backing
Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability Lifetime Tuft Bind Lifetime Edge Ravel Flammability









This cushion-back carpet tile product is covered by one or more patents, published applications and/ or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.