

MODERN BLISS

Cross Tweed

Modular Tile

Construction

Tufted, Textured Loop

Tile Size

50 cm x 50 cm (19.7" x 19.7")

Yarn Type

Universal Fibers® Silkworks SDN Type 6,6 and 6

Stain Repel / Stain Resist / Soil Release

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Solution Dyed

Tufted Face Weight

36 oz/yd² (1221 g/m²)

Gauge

1/12

Stitches Per Inch

10.0

Tufts

120/in² (1,859/100 cm²)

Finished Pile Height

0.19" (4.83 mm)

Finished Pile Thickness

0.15" (3.68 mm)

Average Density (Finished)

?7600

Standard Backing

PVC-Free Comfort Plus® ES Cushion
Available with TractionBack®

Recycled Content by Total Weight

ES Backing: 39.6% Pre-Consumer,
0.0% Post-Consumer
ESP Backing: 31.2% Pre-Consumer,
8.5% Post-Consumer

Nominal Total Thickness

0.42" (10.7 mm)

Nominal Total Weight

124.0 oz/yd² (4,204 g/m²)

Flammability (Radiant Panel

ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care
Service Network

Indoor Air Quality—CRI Green Label Plus™

GLP7205, Carpet Category 13X

Recommended Installation Method(s)

Monolithic, Ashlar

WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®)

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.