

TEST REPORT

DATE: 01-09-2014TEST NUMBER: 0204498

CLIENT	Masland Carpets

Surface Flammability of Carpets and Rugs (16 CFR Chapter II, Subchapter D, Part 1630 CPSC FF 1-70) also referenced as ASTM
D2859



DESCRIPTION OF TEST SAMPLE					
IDENTIFICATION	7867 Vitality				
ROLL NUMBER	878588				
CONSTRUCTION	Multi-Level Loop Pile				
FIBER	100% Universal Fibers Type 6,6 Nylon				
BACKING	Action Bac				

GENERAL PRINCIPLE

This test method is intended to measure the response of finished textile floor covering materials when exposed to an ignition source under controlled laboratory conditions. It is applicable to all types of textile floor coverings whether constructed from natural or man-made materials.

TEST CRITERION

The uncharred area of the test specimen must be greater than one inch in at least seven of the eight specimens tested in order to meet the acceptance criterion.

TEST RESULTS

	SPECIMEN NUMBER									
	1	2	3	4	5	6	7	8		
Uncharred Area (Inches)	3.6	3.6	3.5	3.5	3.7	3.5	3.5	3.6		

NOTE: This sample was tested on the face side.

This sample PASSES the Federal Flammability Standard DOC FF 1-70.

APPROVED BY:

y alwy NVI

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us