

# Independent Textile Testing Service, Inc.

P.O. Box 1948

1503 Murray Ave

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: ittslab@dalton.net

## TEST REPORT

Customer: Masland Carpets, Inc.

April 9, 2004

Subject: Specimens of the submitted sample were prepared and tested in accordance with  
ASTM E 648-03 and/or Federal Test Method 372. NFPA 253

**FLOORING RADIANT PANEL TEST****Sample Description**

Style: 122FA - DIVIDEND  
Color: L460A  
Roll #: R270904A  
Back: AB


**Test Assembly**

Mounted on 6mm FRC Board  
(Using Parabond M4099 Adhesive)

<u>Test Results</u>	<u>Specimen No. 1</u>	<u>Specimen No. 2</u>	<u>Specimen No. 3</u>
Critical Radiant Flux	.60 watts/cm <sup>2</sup>	.46 watts/cm <sup>2</sup>	.48 watts/cm <sup>2</sup>
Total Burn Length	33.0 cm	42.0 cm	43.0 cm
Flame Front Out	48.0 minutes	63.0 minutes	64.0 minutes

**Average Critical Radiant Flux**.51 watts/cm<sup>2</sup>**Estimated Standard Deviation**0.08 watts/cm<sup>2</sup>

14.8% coefficient of variation

  
L. Kent Suddeth

Executive Vice President

Our letters and reports are for the exclusive use of the customer to whom they are addressed, and their communication to any others or the use of the name of Independent Textile Testing Service, Inc., must receive our prior written approval. Our letters and reports apply only to the sample tested and are not necessarily indicative of the qualities of apparently identical or similar products. The reports and letters and the name of the Independent Textile Testing Service, Inc., are not to be used under any circumstances in advertising to the general public.