Test No: 247721



PO Box 1948

1503 Murray Ave

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: ittslab@dalton net

TEST REPORT

Customer: Masland Carpets, Inc. April 9, 2004

Subject: Sample(s) of carpet submitted for testing by the customer and identified below:

Sample Identification: Style: 122FA

Color: L460A Roll #: R270904A

Back: AB

Test Method Conducted AATCC 134-1996 Electrostatic Propensity of Carpets

Purpose and Scope

This test method is designed to assess the static generating propensity of carpets developed when a person walks across them by controlled laboratory simulation of conditions which may be met in practice, and more particularly, with respect to those conditions which are known from experience to be strongly contributory to excessive accumulation of static charges.

Test Conditions:

Chamber Temperature: 70° F. **Chamber Relative Humidity: 20%**

Test Results:	Sole	Underlay	Maximum Voltage 1 (kV)	Maximum Voltage 2 (kV)	Averages (kV)
Test I Step Test	Neolite	H/J	Pos. 0.7	Pos. 0.9	Pos. 0.8
Test II Scuff Test	Neolite	H/J	Neg. 1.0	Neg. 1.2	Neg. 1.1
Test III Step Test	Leather	H/J	Pos. 1.0		
Test IV Scuff Test	Leather	H/J	Pos. 1.1		and was

Soles:

- a) Neolite XS 664
- b) Suede Leather

Underlayment:

- a) Plate: Earth grounded metal plate
- b) H/J: Standard 40 oz./yd2 rubberized Hair/Jute cushion

Executive Vice President