

# S-235 Sheet Flooring Premium Adhesive



**CAUTION**

S-235

**EYE AND SKIN IRRITANT**

## STIR WELL BEFORE USING.

For use with the following Installation

System:

- Residential Felt-Backed

## DESCRIPTION:

<b>Type:</b>	Water-based rubber resin
<b>Color:</b>	Cream
<b>Taggants:</b>	Yes — 50% yellow and 50% orange
<b>Trowel:</b>	S-891 Notched Steel Trowel or S-892 Replaceable Blade Trowel with S-893 Regular Notch or S-894 Fine Notch Blades Porous subfloors: Regular notch — (1/16" deep, 1/16" wide, 3/32" apart), U-notch Nonporous subfloors or existing resilient floors: Fine notch — (1/32" deep, 1/16" wide, 5/64" apart), U-notch
<b>Coverage:</b>	Regular notch: 125–150 sq. ft./gal (12–14 sq. m) Fine notch: 225–275 sq. ft./gal (20–25 sq. m)
<b>Units:</b>	1 quart (0.946 L); 1 gallon (3.78 L) and 4 gallons (15.14 L)
<b>Open Time:</b>	Porous subfloors (wood, concrete) — 0 to 20 minutes Nonporous subfloors (existing flooring) — 10–20 minutes
<b>Working Time:</b>	Up to 40 minutes (May vary based on job conditions, substrates, temperature and humidity)
<b>Shelf Life:</b>	1 year, unopened
<b>Freeze/Thaw Stable:</b>	Yes, to 10° F (-12° C)
<b>VOC Content:</b>	<2 g/L; calculated and reported, SCAQMD 1168
<b>Clean Up:</b>	Wet — clean, white cloth with neutral detergent and water Dry — clean, white cloth and mineral spirits
<b>Subfloors:</b>	All grade levels of concrete, existing resilient floors, ceramic, terrazzo, marble, steel, stainless steel, aluminum, lead, copper, brass, bronze, polymeric poured floors and approved suspended wood Radiant heated subfloors where the surface temperature does not exceed 85° F (29° C)
<b>Advantages:</b>	Strong, fast initial grab (helps prevent edge curl) Moisture and alkali resistant Excellent bond integrity Solvent-free and low odor