

TEST RESULTS SURFACE BURNING CHARACTERISTICS



Korogard 500 Wallcoverings intended for application with the specified adhesive in accordance with instructions accompanying the product.

Applied to Inorganic Reinforced Cement Board

| | .050" (1.27mm) or Less* | .060" (1.52mm) or Less* | .093" (2.36mm) or Less* |
|-----------------|-------------------------|-------------------------|-------------------------|
| Flame Spread | 25 | 20 | 35 |
| Smoke Developed | 40 | 350 | 350-450 |
| | .028" (.71mm) ++ | .50" (12.7mm) or Less++ | |
| Flame Spread | 20 | 20 | N/A |
| Smoke Developed | 140 | 250 | |

Korogard 600 Wallcoverings intended for application with the specified adhesive in accordance with instructions accompanying the product.

Applied to Inorganic Reinforced Cement Board

| | .050" (1.27mm) or Less* | .060" (1.52mm) or Less* |
|-----------------|-------------------------|-------------------------|
| Flame Spread | 20 | 20 |
| Smoke Developed | 130-175 | 250 |

* Applied with Minnesota Mining & Manufacturing's "Fastbond™ 30-NF or 3M #30 Nonflammable Contact Cement" adhesive at an application rate of 130 sq. ft. per gallon.

++ Applied with Super-Tek Products, Inc.'s "K-Bond" adhesive at an application rate of 80 sq. ft. per gallon.