

Braided #11439

Product Specification

Face Construction	Imperial	Metric				
Construction	Stratatec® Patterned Loop					
Face Weight	17 oz/sq yd	576.3 g/sq m				
Gauge	5/64	50.4 rows/10 cm				
Stitches per Inch	10.9	42.9 pu/10 cm				
Tuft Density	139.5 tufts/sq in	21.6 tufts/sq cm				
Pile Height Average	0.110 inch	2.8 mm				
Pile Thickness	0.072 inch	1.8 mm				
Density Factor	8,500 oz/cu yd	314.5 kg/cu m				
Fiber System	Dynex SD® Nylon (Permanent Stain Resistance)					
Dye Method	100% Solution Dyed					
Fluorine-Free Soil Protection	Eco-Ensure	7.6 Kilotex				
Primary Tufting Substrate	Synthetic Non-Woven					
Pattern Match	Not Required					

Third Party Environmental Certifications

	Product	Recycled Content*		NSF 140	Cradle to Cradle
		Overall	Postconsumer	SCS Certified	Certified™ v3.1**
Certified	ethos® Modular with Omnicoat Technology®	47-75%	28%	Platinum	Silver
Certified	Flex-Aire Modular® Cushion	21-41%	4%	Gold	

^{*}Minimum recycled content certified by Scientific Certification Sytems (SCS) and varies by product style.

Product Testing/Information

Electrostatic Propensity 0.9 kV (AATCC 134); Permanent Conductive Fiber

Surface Flammability Passes CPSC FF 1-70 (ASTM D-2859)

Flooring Radiant Panel Class 1 (mean average CRF: 0.45 w/sq cm or higher) (ASTM E-648)

 Smoke Generation
 Less than 450 (ASTM E-662)

 Colorfastness to Light
 ≥ 4 after 100 hours (AATCC 16E)

 Soil Protection
 Application Rate: 2% of Face Weight

Stain Resistance ≥ 8 (AATCC 175-08 Stain Resistance Pile Floor Coverings)

Installation Methods

Peel and Stick RS Adhesive System - Full Coverage Peel & Stick

Wet Spread Backing specific Tarkett Adhesives

Installation Method 24" x 24" Vertical Ashlar, Pivot (Vertical/Quarter Turn): 18" x 36", 9" x 36" Vertical Ashlar, Herringbone

Product Notes

- 1. Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice. Colors may vary slightly from dye lot to dye lot.
- 2. U.S. Patent numbers: 4,849,267; 6,406,574, US 9,988,760 B2
- 3. Chair pads are recommended for optimum textural performance. Absent the use of chair pads, more intensive maintenance will be required for areas in direct contact with chair caster traffic, and some degree of appearance change is to be expected.

Tarkett North America

Technical Services Department 1735 Cleveland Hwy Dalton, GA 30721 800.248.2878 Fax 706.259.2621 info@tarkettna.com

www.tarkettna.com

^{**}Cradle to Cradle Certified is a certification mark licensed by the Cradle to Cradle Products Innovation Institute



IMPERIAL METRIC TEST METHOD

Warranty: Lifetime limited warranty against excessive surface wear, static, delamination, edge ravel, zippering, backing resiliency loss & stain resistance.

SCS Certified total 47-75%

CERTIFIED

cradle to cradle

SILVER

Cradle to Cradle Certified™ v3.1

SCS Certified

SCS Certified

SCS Certified

ethos® Modular with Omnicoat Technology®

Total Minimum Recycled Content
Pre-Consumer
Postconsumer
Third Party Certification NSF-140

58.7%
23.9%
34.8%
Platinum

Cradle to Cradle Certification Silver (Certification #1904)

Product Size 24" x 24" Tile (9" x 36" and 18" x 36" also available)

Secondary Backing 50% Recycled Content

Intermediate Layer Fiberglass Reinforced Sealant Product Construction No Delamination per ASTM D-3936

Secondary Backing Density65.0lbs/cu ft1041kg/cu mSecondary Backing Thickness0.050inch1.3mmTotal Weight94.9oz/sq yd +/-5%3216.8g/sq m

CRI Green Label Plus Certification GLP8320



Total Minimum Recycled Content 25.4% SCS Certified total 21-41%

Pre-Consumer19.7%SCS CertifiedPostconsumer5.8%SCS CertifiedThird Party Certification NSF-140GoldSCS Certified

Product Size 24" x 24" Tile (9" x 36" and 18" x 36" also available)
Secondary Backing Fiberglass Reinforced Composite Closed Cell Cushion

Intermediate Layer Fiberglass Reinforced Sealant
Product Construction No Delamination per ASTM D-3936

Cushion Weight 35.5 oz/sq yd 1203 g/sq m **ASTM D1667 Cushion Density** 18.5 lbs/cu ft 296 kg/cu m **ASTM D1667 Cushion Thickness** 0.156 inch 4.0 **ASTM D1667** mm

Total Weight with RS / Non-RS 116.1 114.7 oz/sq yd +/-5% 3937 3890 g/sq m

Compression Set Max. 10% ASTM D1667 Compression Deflection 5 Min. 25 max lbs/sq inch @ 25% 352 1758 g/sq cm ASTM D1667

CRI Green Label Plus Certification GLP6558

Powerbond® Cushion

Total Minimum Recycled Content
Pre-Consumer
Postconsumer
Third Party Certification NSF-140
Product Size

8.6%
Gold
Fr.

Cushion Closed Cell Cushion

Heterogeneous Construction No Delamination per ASTM D-3936

Cushion Weight g/sq m **ASTM D1667** 35.5 oz/sq yd 1203 **Cushion Density** 296 18.5 lbs/cu ft kg/cu m **ASTM D1667 Cushion Thickness** 0.156 inch 4.0 **ASTM D1667** mm

Total Weight with RS / Non-RS 78.0 75.7 oz/sq yd +/-5% 2646 2568 g/sq m

Compression Set Max. 10% ASTM D1667 Compression Deflection 7 Min. 25 max lbs/sq inch @ 25% 492 1758 g/sq cm ASTM D1667

CRI Green Label Plus Certification GLP9744

Powerbond Medfloor®

Total Minimum Recycled Content 9.1%
Pre-Consumer 0.0%
Postconsumer 9.1%
Product Size 6 ft.
Cushion Medfloor

Heterogeneous Construction No Delamination per ASTM D-3936

Cushion Weight oz/sq yd 1254 g/sq m **ASTM D1667** 37 Cushion Density 30 lbs/cu ft kg/cu m **ASTM D1667** 481 0.085 2.2 **Cushion Thickness** inch mm **ASTM D1667**

oz/sq yd +/-5%

Total Weight 77.2

Compression Set Max. 10% ASTM D1667
Compression Deflection 29 Ibs/sq inch @ 25% 2039 g/sq cm ASTM D1667

CRI Green Label Plus Certification GLP9744

800.248.2878 www.tarkettna.com © 2021 Tarkett USA Inc. 11/2021

2618

g/sq m