

Model: TAJ MAHAL POLISHED 47"X47" approx.

Codes: 100331136

Absorption: Bla - Porcelánico ($E \leq 0.1\%$)



DIMENSIONAL FEATURES

Length	47 1/4" approx	
Thickness	1/4" approx	
Width	47 1/4" approx	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

MECHANICAL FEATURES

Breaking strenght	1118.5 N	
Modulus of rupture	43.6 N/MM2	
Crack resistance	RESISTE 3 CICLOS	

HYGIENIC FEATURES

Chemical resistance	MÍNIMO CLASE B	
Stain resistance	CLASE 5	

ANTI-SLIP VALUE

Slip resistance (pendulum-wet)	CL0	
Slip resistance (pendulum-dry)	>40**	

PACKING

Sales units per box	31 SQF/CS	
Sales units per pallet	868.06 SQF/PAL	
Sales units per unit	15.5 SQF/ST	

SCOPE OF USE

Technical code-1	3 - Light traffic with no direct access to the outside	
Technical code-2	0 - No additional requirements	

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

RECOMMENDED USE LOCATIONS

Single-family dwelling

Indoor Premises - Dry: Room, room, bedroom or other enclosure without direct access to the outdoors.

Collective housing

Indoor Premises - Residential - Dry: Entrance, living room, dining room, professional office with reception of customers

Indoor Premises - Housing - Dry: Bedrooms, personal office, storage room, changing room

Various

Cladding of bonded or mixed facades

Facade cladding with mechanical anchors

Kitchen worktops, bars, restaurants

Public bathroom countertops

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.