L'ANTIC COLONIAL

Model: LINKFLOOR EMPIRE CREAM

Codes: 100203327 Group: G-234

Format: 9"X70 111/128"X19/64" approx.



COMPOSITION Size Material Type of material Layer 1 0.5 Wear layer Use layer with PU protection Layer 2 Vinyl vinyl decorative layer 0.9 Elastic PVC Intermediate comfort laver Layer 3 Layer 4 4.5 WPC WPC composite body Layer 5 EVA EVA rubber base plate

Floorscore certification FLOORSCORE

ADDITIONAL NOTES

In installations with underfloor heating the temperature must not exceed 27

FEATURES



Texture similar to brushed wood



Water and moisture resistant flooring, suitable for wet areas such as bathrooms and kitchens for residential use, provided the product's installation instructions are followed.



5 year warranty for commercial use valid for vinyl materials that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with ISO 10582.



Floor capable of dissipating excess electrical charges and distribute them over its entire surface $\,$



Installation system where gluing the boards to the floor is not necessary. They are placed on a foam, joined together, as long as the product does not already have a foil on the back of the piece.



15 year home use warranty valid for vinyl materials that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use category in accordance with ISO 10582.



Is suitable for installing on water radiant heating



There are slight color changes between pieces.





LINKELOOR EMPIRE CREAM

L'ANTIC COLONIAL

LABORATORY TESTS									
Commercial area class	33								
Slip resistance (r)	R-10	DIN 51130*							
Abrasion resistance	≤0.015g/1000 circles	EN 660-1:99*							
Furniture leg effect	≤0.015 g/1000 ciclos	EN 424*							
Castor chair effect	No damage %								
Swelling in thickness	±0.2 MM	ISO 24336*							
Slip resistance (pendulum-wet)	CL 1 (17)	UNE 41901*							
Tensile strength of joints	Longitudinal: F0.2=2.35 kN/m; Transversal: F0.2=1.90 kN/m	ISO 24334*							
Fire resistance	Bfl-S1	EN13501-1*							
Evaluation of propensity to accumulation of electrostatic charges	≤2 kV	EN 1815*							
Heat resistance	0.064 M2*K/W	EN 12664*							
Fungus test	1	ASTM G21:96*							
Residual footprint	Average=0.08 mm; max=0.092 mm	ISO 24343-1*							
Dynamic coefficient of friction	0.44	ANSI A137.1*							
Impact resistance	No damage KGF/MM2								
Private area class	23								
Slip resistance (pendulum-dry)	CL 3 (98)	UNE 41902*							

	PACKING
Sales units per box	17.72 SQF/CS
Sales units per pallet	1133.86 SQF/PAL
Sales units per unit	4.43 SQF/ST
Sale unit	M2
Base unit	ST
Sales units per square meter	1 M2
Net weight	182.24 LB/SQF
Gross weight	193.14 LB/SQF

SPECIAL PIECES												
SAP	Description	Group	Boxes	Pallet	Units	SKU	Basic Unit	Net Weight	Gross weight			
100233699	MAMPER LINKFLOOR EMPIRE CREAM 7X120X3	G-163	2 PIECES/BOX	200 PIECES/PAL	11.9 PIECES/M2	-	-	0.58 KG/PIECES	1.64 KG/PIECES			
100211756	PERFIL ADH LINKFLOOR EMPIRE CREAM 3,5	G-155	20 PIECES/BOX	1000 PIECES/PAL	9.26 PIECES/M2	-	-	0.77 KG/PIECES	0.8 KG/PIECES			
100211774	ZOCALO LINKFLOOR EMPIRE CREAM 8X220X1,5	G-121	14 PIECES/BOX	560 PIECES/PAL	5.68 PIECES/M2	-	-	1.33 KG/PIECES	1.38 KG/PIECES			





It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A.U., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.U.

28/06/2024