

| **Acrovyn® 4000 Wall Covering Physical Properties**

TYPICAL PHYSICAL PROPERTIES
Acrovyn .040"/.060"/.075" WALL COVERING

PROPERTY	TEST METHOD	TYPICAL VALUE
Specific Gravity	ASTM D-792	1.31
Tensile Strength ASTM D-638 5,715 psi	Flexural Strength ASTM D-790	7,024 psi
Flexural Modulus	ASTM D-790	242,000 psi
Hardness (Shore D)	ASTM D-785	71
Heat Distortion Temp.	ASTM D-648	150.4° F