Flammability Certificate 9501 Wonder Designtex

9501 Wonder was tested and met the following flammability requirements:

CA TB 117-2013



719 century ave sw • grand rapids, mi 49503 p. 616.369.0522 e. info@flooralytics.com



report number est-2268 revision level original report date 2.15.2023

certificate of testing

client Designtex

200 Hudson St.

9th Floor

New York, NY 10013

product identification

9501 Wonder

test method performed

smolder resistance of materials used in upholstered furniture – section 1: cover fabrics

california technical bulletin 117: 2013 (january 2019 revision)

date of test 2.15.2023

test results

specimen	char length (in.)	extinguished <45 min (y/n)
1	self-extinguished	У
2	0.5	У
3	0.5	У

notes

test conditions 70 ±3.5°f, 50 ±5% relative humidity requirement: 21 ±3°c, less than 55% relative humidity

sampling as received ignition source srm1196a deviations none

acceptance criteria

pass • vertical cha

- vertical char length ≤1.8 inches (45mm)
- smoldering extinguishes within 45 minutes
- no transition to open flaming
- fail vertical char > 1.8 inches (45mm)
 - smoldering beyond 45 minutes
 - specimens transition to open flaming

retest

- if only one of the three initial specimens fail, retest an additional three specimens
- if all three additional specimens pass the test, the cover fabric passes the test
- if any one of the additional three specimens fail, the cover fabric fails the test

classification

based upon the test results and acceptance criteria listed above, the product identified is a

 $\ensuremath{\boxtimes}$ pass

 $\; \square \; \mathsf{fail}$

☐ requires retesting

certification statement by signing below, the lab certifies that the results were obtained after testing specimens submitted by the client in accordance to the procedures and equipment specified by the standard stated above.

approved by:



This report is confidential and prepared for the exclusive use of the client to whom they are addressed. It may not be reproduced or published without prior written approval. The results apply only to the samples tested may not necessarily reflect product performance under actual use. The results are representative of similar goods only to the extent that the sample tested is representative of those goods.

page 1 / 1 doc rev 4.15.21